

# Data Sheet Advanced-PP 1100 N

## **Description**

Advanced-PP 1100 N is a medium flow polypropylene homopolymer for general injection molding applications.

# **Application**

Closures, Furniture, Housewares, General injection molding.

#### **Regulatory Information:**

The grade Advanced-PP 1100N and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011 (and its amendments). Specific information is available upon request.

## **Properties (Typical values)**

Properties	Unit	Test method	Value	
Melt Flow Rate				
Melt flow rate (230°C / 2.16 KG)	g / 10 min	ISO 1133	12	
Mechnical Properties				
Tensile modulus of elasticity (v= 1 mm/min)	MPa	ISO 527-2	1550	
Tensile stress at yield (v= 50 mm/min)	MPa	ISO 527-2	35	
Tensile strain at yield (v= 50 mm/min)	%	ISO 527-2	8	
Tensile strain at break (v= 50 mm/min)	%	ISO 527-2	>50	
Charpy impact strength unnotched (+23°C)	kJ/m <sup>2</sup>	ISO 179/1eU	110	
Charpy impact strength notched (+23°C)	kJ/m <sup>2</sup>	ISO 179/1eA	3.0	
Izod Impact strength notched (+23°C)	kJ/m <sup>2</sup>	ISO 180/1A	3	
Ball indentation hardness ( H 358/30)	MPa	ISO 2039-1	78	
Thermal Properties				
Melting point, DSC	°C	ISO 3146	163	
Heat deflection temperature HDT/B ( 0.45 Mpa)	°C	ISO 75-2	85	
Vicat softening temperature VST/A50 (10 N)	°C	ISO 306	154	
Other Properties				
Density	g / cm <sup>3</sup>	ISO 1183	0.91	
alues given here are typical and should not be interpreted as spe nd application, these data do not relieve the receiver to this inforr either do they imply any legally binding assurance of certain prop ith or on the basis of the information in this publication.	mation from the respo	onsibility of carry out their o	wn test and experiments;	
			Mar'20	
Advanced Petrochemical Company Saudi Joint Stock Company		الشركة المتقدمة للبتروكيماويات شركة مساهمة سعودية		
Headquarters - Dammam P.O. Box 7215 Dammam 31462 Saudi Arabia Jubail P.O. Box 11022 Jubail 31961 Saudi Arabia Tel: +966 13 359 1000 Fax: +966 13 356 6065 C.R. 2055008094 Paid up capital: S.R. 1,967,940,000.00	г	المركز الرئيسي - الدمام ص.ب. ٢٢١٥ - الدمام ١٣١٢٣ المملكة العربية السعودية الجبيل ص.ب. ١١.٢٢- الجبيل ١٣٩١ المملكة العربية السعودية هاتف: ١١ ٢٩٣٩ ١٣٦٢+ فاكس: ٢٠٦.٢٦٣٩ ١٣٦٢+ س.ت. ٢.٥٥.٨.٩٤ رأس المال المدفوع:١٩٦٧,٩٤.		

www.advancedpetrochem.com