

QAMAR FC21HN

Linear Low Density Polyethylene
SPDC Ltd.

Technical Data

General

Material Status	• Commercial: Active
Literature ¹	• Technical Datasheet (English)
Availability	• Africa & Middle East • Asia Pacific • Europe • North America
Additive	• Antiblock • Slip
Features	• Antiblocking • General Purpose • Medium Clarity • Slip
Uses	• Film • General Purpose
Forms	• Pellets
Processing Method	• Blown Film

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.918 g/cm ³	0.918 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0 g/10 min	1.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress			JIS K6760
Yield	1740 psi	12.0 MPa	
Break	4640 psi	32.0 MPa	
Tensile Strain (Break)	900 %	900 %	JIS K6760
Apparent Bending Modulus	37700 psi	260 MPa	ASTM D747

Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Film Thickness - Tested	1.2 mil	30 µm	
Tensile Modulus			ISO IR 1184
MD: 1.2 mil (30 µm)	27600 psi	190 MPa	
TD: 1.2 mil (30 µm)	31900 psi	220 MPa	
Tensile Stress			JIS Z1702
MD: Break, 1.2 mil (30 µm)	7980 psi	55.0 MPa	
TD: Break, 1.2 mil (30 µm)	5800 psi	40.0 MPa	
Tensile Elongation			JIS Z1702
MD: Break, 1.2 mil (30 µm)	550 %	550 %	
TD: Break, 1.2 mil (30 µm)	850 %	850 %	
Dart Drop Impact (1.2 mil (30 µm))	120 g	120 g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 1.2 mil (30 µm)	30 g	30 g	
TD: 1.2 mil (30 µm)	160 g	160 g	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	55	55	ASTM D2240

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	< -94.0 °F	< -70.0 °C	ASTM D746
Vicat Softening Temperature	216 °F	102 °C	ASTM D1525
Melting Temperature	252 °F	122 °C	DSC

Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Haze (1.18 mil (30.0 µm))	11 %	11 %	ASTM D1003

Extrusion	Nominal Value (English)	Nominal Value (SI)
Melt Temperature	374 to 410 °F	190 to 210 °C
Melt Temperature (Aim)	392 °F	200 °C

Extrusion Notes

Blow up Ratio: 2 to 4
Screw Type: LLDPE screw
Die Lip Gap: 2.0 to 3.0 mm
Air Ring: Single or Dual Slit (Wide die)

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.

Where to Buy

Supplier


SPDC Ltd.
, Japan
Web: <http://www.spdc.co.jp/>

Distributor

Please contact the supplier to find a distributor for QAMAR FC21HN



Founded in 1986 and based in Laramie, Wyoming, IDES is now part of the UL family of companies. UL is a premier global independent safety science company with more than a century of proven history. Employing nearly 10,000 professionals in over 100 countries, UL has five distinct business units -- Product Safety, Environment, Life & Health, Knowledge Services and Verification Services -- to meet the expanding needs of our customers and to deliver on our public safety mission.



Prospector Plastics Database - www.ides.com/prospector

Prospector is a searchable online database that includes 85,000 data sheets from 875 manufacturers and 44,000 UL yellow cards. Each data sheet includes property, processing and supplier contact information. Prospector is relied on by nearly 400,000 design engineers and plastics processors. Using Prospector, they save time with plastic material selection by quickly and easily referencing technical information critical to the success of their products.

"Prospector is absolutely the best and most well-known search engine for plastic raw materials in the world. We use Prospector every day – it's a real time saver!"

– Birgit Elvardt Bader, Production Manager, Micotron

Power Searches

Property Search – select plastics by 500 key properties and design parameters.

Alternative Resins Search – find replacement plastics within minutes.

Automotive Plastics Search – easily locate automotive approved plastics.

Curve Data – view, overlay and export curve data.



Material Data Management – www.ides.com/datasheets

With our data management services, plastic suppliers and distributors can have custom search interfaces available on their website for their customers, website visitors, sales and customer service teams. These provide intuitive ways to find and view technical data sheets for their products.

"With UL IDES data services, our website now displays the most current information on the products we distribute and links to our backend RFQ and sales order system, adding both value and service for our customers."

– Kevin Chase, Owner & President, Chase Plastics



Advertising – www.ides.com/advertise

Reach 365,000 pre-qualified plastics professionals and generate leads with proven techniques. Electronic newsletter insertions, sponsored webinars and powerful online ads are available to make the most of your lead-generation program.



For more information, call: 800.788.4668 or 307.742.9227 ext. 220